

CAUTION: THE STONE MUST BE SEASONED BEFORE USE OR THE STONE WILL EXPLODE!

Heat the stone with care for the first time!! During transportation, the stone may absorb moisture. Ensure the stone is fully air dried before starting the seasoning process. Once seasoned, the stone can be used freely.

First use of the oven with stone hearths:

1. Do not turn on the bottom heat while completing this process. Set the bottom temperature to "0" Celsius and then set the top temperature to 100°C.
2. After "Top" temperature reaches to 100°C, increase the temperature by 25°C every 15 minutes until you reach 250°C. Leave the oven on 250°C for 15 minutes before continuing.
3. Turn off the oven and cool the oven chamber to ambient temperature (below 38°C) or cool the oven about 8 hours.

Second Drying Procedure:

1. Turn on the power.
2. Set the top and bottom temperature to 100°C.
4. After "Top & Bottom" temperature reaches to 100°C, increase the temperature step by step from 25°C to 250°C. Increase the temperature by 25°C every 15 minutes until you reach 250°C. Leave the oven on 250°C for 15 minutes before continuing.
3. After drying the ovens, you can use the oven with stone freely.